



POLYCARBONATE SAPHIR[®] FC

POLYCARBONATE SAPHIR[®] FC is our range of polycarbonate coated sheet.

POLYCARBONATE SAPHIR[®] FC, Formable Coating, polycarbonate sheet with a unique heat formable coating for curved applications.

POLYCARBONATE SAPHIR[®] FC is a coated polycarbonate sheet, glass like in appearance. The high impact strength of polycarbonate is combined with a flexible heat formable coating for curved applications, improved chemical resistance and good protection against abrasion.

POLYCARBONATE SAPHIR[®] FC can be heat formed and is suitable for curved applications.

POLYCARBONATE SAPHIR[®] FC, is produced to fulfill the EN 166. Standard for visor products.

ALSO AVAILABLE:

One side coating, Anti-fog coating on one side, any transparent colour.

POLYCARBONATE SAPHIR[®] FC BENEFITS:

- Heat forming / Drape forming properties
- Abrasion and Chemical resistant
- High heat resistance and dimensional stability
- More than 10 times the impact strength of high impact Acrylic

APPLICATION AREAS:

Curved applications, Visors for motorcycle, industrial visors and goggles, police helmet visors and multiple indoor and non-permanent outdoor applications.

DELIVERY PROGRAM:

Maximum size: 2000x3000 mm

Thickness range: 1 – 6 mm

1 side or 2 side coated

Special sizes and thicknesses on request.

POLYCARBONATE SAPHIR® FC TYPICAL PROPERTY VALUES

Property	Value	Unit	Standard
Physical properties			
Density	1,2	g/cm ³	ISO 1183
Refractive index (20 °C)	1,586		ISO 489
Moisture absorption 24 h, 23 °C, 50% RH	0,15	%	ISO 62
Mechanical properties			
Tensile strength at yield (at break)	60 (70)	N/mm ²	ISO 527
Elongation at yield (at break)	6 (110)	%	ISO 527
Elastic modulus	>2300	N/mm ²	ISO 527
Flexural modulus	>2300	N/mm ²	ISO 178
Charpy unnotched impact strength -40 °C	NB	kJ/m ²	ISO 179/1eU
Charpy notched impact strength -30 °C	11	kJ/m ²	ISO 179/1eA
Izod notched impact strength +23 °C	65	kJ/m ²	ISO 180/1A
Izod notched impact strength -30 °C	10	kJ/m ²	ISO 180/1A
Thermal properties			
Coefficient of linear thermal expansion (20-70 °C)	65x10 ⁻⁶	K ⁻¹	ISO 11359-2
Thermal conductivity	0,20	W/m.K	ISO 8302
Coating properties			
Adhesion	GT-0		DIN 53151 / ISO 2409
Taber Abrasion, CS 10F, 500g, 500 cycles	<9	% Haze	ASTM D1044

Thickness	Bending radius	Unit	Forming
1 – 3 mm	120	mm	Cold / Drape forming
>3 – 6 mm	140	mm	Cold / Drape forming

Properties reported here are typical values for polycarbonate. Arla Plast makes no representation that the material in any particular shipment will conform exactly to the values given. The above information is based upon experience and given in good faith. Due to many factors which are outside our knowledge and control, no warranty is given or is to be implied with respect to such information. Detailed product specification and technical manual/information is available on request.